

i-CLIPS[®].com

ON

63 x 44 x 1984 mm

x 2

PINE
CL4
CTB B+



+/-

2 m²

THERMO

1,2 m²

COMPOSITE



réf. 963



05/2017



CE

1973-CPR-247

BURGER & CIE

ZI Bois L'Abbesse, 68660 Liepvre, France

16

EN 14081-1:2005+A1:2011; NF B 52-001-1

Graded structural timber with rectangular cross-section

PNSY

Dimensions of cross section:

44x63 mm

Classé sec 18%-20%

EN 338+ EN 1995-1 (domestic annex)

C18

Reaction to fire

D – s2, d0

Release of dangerous substances

NPD

Durability “PT” as:

1. Type of treatment and preservative

Autoclave
Tanalith E3474
Classe 4

2. Penetration class

NP5

3. Retention value

16 kg/m3

4. Target biological agents

Fungi, insects,
termites

IN + ON + UP

